



SKAPS TRANSNET™ geonet consists of SKAPS Geonet made from HDPE resin.

| PROPERTY | TEST METHOD | UNIT | VALUE | QUALIFIER |
|-------------------------------|----------------------------|---------------------|------------------------|--------------------|
| Thickness | ASTM D 5199 | mm | 5.08 | MAV ⁽³⁾ |
| Carbon Black | ASTM D 4218 | % | 2.0 | MAV |
| Tensile Strength | ASTM D 7179 | N/mm | 7.87 | MAV |
| Melt Flow | ASTM D 1238 ⁽²⁾ | g/10 min | 1.0 | Maximum |
| Density | ASTM D 1505 | g/cm ³ | 0.94 | MAV |
| Transmissivity ⁽¹⁾ | ASTM D 4716 | m ² /sec | 2.0 x 10 ⁻³ | MAV |

Notes:

1. Transmissivity measured using water at 21 ± 2 °C (70 ± 4 °F) with a gradient of 0.1 and a confining pressure of 479 kPa between steel plates after 15 minutes. Values may vary with individual labs.
2. Condition 190/2.16
3. Minimum average value

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.